



# Kriebcoat Superior Coldset

## TYPICAL END USES

Web offset coldset - standard and waterless  
for flyers, magazines, catalogues, newspapers

## COLOUR PROFILE

## FINISH

mat surface

## PRINTING METHODS

Coldset

## TECHNICAL DATASHEET (Target values)

Substance	ISO 536	g/m <sup>2</sup>	48	51	54	57	60	65	70	80	90*
Brightness	ISO 2470	%	78	78	79	79	79	79	79	79	79
Opacity	ISO 2471	%	96	96	96	96	96	97	98	98	98
Gloss (Gardner 75°)	Tappi 480	%	10	10	10	10	10	10	10	10	10
Smoothness Bekk	DIN 53107	sec	60	60	60	60	60	60	60	60	60
Bulk	ISO 534	cm <sup>3</sup> /g	1,20	1,20	1,20	1,20	1,20	1,20	1,20	1,20	1,20

\*on demand

## REEL SPECIFICATIONS

Cores: 70 mm, 76 mm, 150 mm  
Trimmed width: 3780 mm  
Width: min. 340 mm, max. 2860 mm  
Diameters: min. 1000 mm, max. 1250 mm  
Max. Weight: 3900 kg

## ENVIRONMENT

100% sustainable fibers and sources  
No chlorine bleaching in production process  
Recyclable paper  
Recyclable packaging materials

## CERTIFICATES

FSC®  
PEFC™  
Blauer Engel RAL-UZ 72  
EU Ecolabel

## STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19 °C and 23 °C.
- If the paper is stored in non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.

Kübler & Niethammer Papierfabrik Kriebstein AG  
Bauhofstraße 1  
OT Kriebethal, 09648 Kriebstein  
Tel +49 (0) 34327 97-50  
info@k-n-paper.de