

Kriebcoat Superior Silk



TYPICAL END USES

Web offset heatset
for flyers, magazines, catalogues

COLOUR PROFILE

FINISH

silk mat surface

PRINTING METHODS

Heatset

TECHNICAL DATASHEET (Target values)

Substance	ISO 536	g/m ²	48	51	54	57	60	65	70	80	90*
Brightness	ISO 2470	%	78	79	80	80	80	80	80	80	80
Opacity	ISO 2471	%	93	93	94	94	94	95	96	98	98
Gloss (Gardner 75°)	Tappi 480	%	20	20	20	20	20	20	20	20	20
Smoothness Bekk	DIN 53107	sec	325	325	350	350	350	350	350	350	350
Bulk	ISO 534	cm ³ /g	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00

*on demand

REEL SPECIFICATIONS

Cores: 70 mm, 76 mm, 150 mm
Trimmed width: 3780 mm
Width: min. 340 mm, max. 2860 mm
Diameters: min. 1000 mm, max. 1250 mm
Max. Weight: 3900 kg

ENVIRONMENT

100% sustainable fibers and sources
No chlorine bleaching in production process
Recyclable paper
Recyclable packaging materials

CERTIFICATES

FSC®
PEFC™
Blauer Engel RAL-UZ 72
EU Ecolabel

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19 °C and 23 °C.
- If the paper is stored in non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1
OT Kriebethal, 09648 Kriebstein
Tel +49 (0) 34327 97-50
info@k-n-paper.de