

NeoPress O Gloss

TYPICAL END USES



Catalogues



Magazines



Brochures



Books



Direct mailing

COLOUR PROFILE

☑ FOGRA 46L.txt
☑ PSO_LWC_Standard.
eci.icc

FINISH

☑ Gloss

PRINTING METHODS

☑ HSWO

TECHNICAL DATASHEET (TARGET VALUES)

Substance		g/m ²	48	51	54	57*		
Brightness	D65/10°	%	73	73	74	74		
Whiteness	CIE, ISO 11476, C2°	%	64	64	64	65		
L*	D65/10°		89	89	90	90		
a*	D65/10°		-0,8	-0,8	-0,8	-0,8		
b*	D65/10°		2	2	2	2		
Opacity	D65/10°	%	87	88	89	90		
Gloss Hunter	ISO 8254-1	%	48	50	52	54		
Thickness	ISO 534	µm	44	46	48	50		
Bulk	ISO 534	cm ³ /g	0,92	0,90	0,89	0,88		
Smoothness	ISO 8791-4 PPS 1MPa	µm	1,2	1,1	1,1	1,1		

Technical specifications are target values and may be subject to production variations.

*on request only



ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials
Sustainable sources



REEL SPECIFICATIONS

Cores: 76 mm, 150 mm
Trimmed width: 7160 mm
Width: min. 388 mm, max. 3200 mm
Diameters: min. 1000 mm, max 1300 mm
Max. Weight: 7000 kg



CERTIFICATES

EU Ecolabel
ISO 9001
ISO 14001
ISO 50001
ISO 45001
FSC® CoC
PEFC™ CoC

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in a non - air conditioned warehouse, it is absolutely necessary to allow a stabilization period in the print room.
- Open the protective wrapping at the moment of use.



Kabel Premium Pulp & Paper GmbH

Schwerter Straße 263
58099 Hagen
Tel +49 (0) 2331 699-0
sales@kabelpaper.de

